



TECHNICAL DATA

DESCRIPTION	TEST METHOD	NEOFL Looselay 0.50/4.5T RESULT
Overall Thickness	KS M 3802	4.49(mm) Pass
Thickness of Wear layer	-	0.50(mm) Pass
Length / Width	KS M 3802	Pass Length : 600.13 (mm) Width : 600.03 (mm)
Dimensional Stability	KS M 3802	Pass Length direction/Machine direction : 0.01 % Width direction/Across machine direction : 0.00 %
Curl		0.00mm
Effect of castor chair	EN ISO 10582 (ISO 4918)	Pass
Wear resistance	EN 660-2	Wear Group : T
Color fastness to light	EN ISO 10582 (ISO 105-B02:2014, Method 3)	≥Grade 6
	ASTM F1515	ΔE*=1.71
Slip Resistance	DIN 51130 (EN 13893)	R10
Chemical Resistance	EN 438-2:2005 section 26	Grade 5
Reaction to Fire	EN 13501-1	Bfl -s1
Fungi Resistance test	ISO 846:1997	Intensity of growth